



Infrastructure Technology

Manuf. & Materials Technology, 14 Julius Ave (Riverside Corp. Park), North Ryde, NSW, 2113, Australia
Telephone: 61 2 9490 8252 Facsimile: 61 2 9490 5777 Email: tiles@csiro.au Web: <http://www.cmse.csiro.au>

Registered Testing Authority - CSIRO

28 May 2013

Our Ref. ES13 / 2239 03/0212

TEST REPORT No. SY6693.3

Requested by: Opie Manufacturing Group Pty Ltd
6 Bromley Road
Emu Plains
NSW 2750

on (date): 23 May 2013

Manufacturer: Opie Manufacturing Group Pty Ltd

Product Desc.: TG3 - Pre Treatment Infloor Channle Drain With Inguilt Arrestor Trap/Kitchen and Food Prep

Sampling details:

Where: Delivered

Date: 23 May 2013

By whom: Courier

How (methods): N/A

The results reported relate only to the sample(s) tested and the information received. No responsibility is taken for the accuracy of the sampling unless it is done under our own supervision. CSIRO cannot accept responsibility for deviations in the manufactured quality and performance of the product. While CSIRO takes care in preparing the reports it provides to clients, it does not warrant that the information in this particular report will be free of errors or omissions or that it will be suitable for the client's purposes. CSIRO will not be responsible for the results of any actions taken by the client or any other person on the basis of the information contained in the report or any opinions expressed in it. The reproduction of this test report is only authorised in the form of a complete photographic facsimile. Our written approval is necessary for any partial reproduction.

This test report consists of 3 pages

SUMMARY OF SLIP RESISTANCE TESTS PERFORMED:

		Result	Class
AS/NZS 4586:2004	Slip resistance classification of new pedestrian surface materials, Appendix D: OIL-WET Ramp		
	Mean overall acceptance angle:	19.9°	R 11 [LOW*]

* = CSIRO classification

In order to interpret the classifications, please refer to Standards Australia Handbook 197, An Introductory Guide to the Slip Resistance of Pedestrian Surface Materials, which recommends minimum classifications for a wide variety of locations.

It is important to realise that test results obtained on unused factory-fresh samples may not be directly applicable in service, where proprietary surface coatings, contamination, wear and subsequent cleaning all influence the behaviour of the pedestrian surface.



REPORT NO: SY6693.3 Page 2 of 3
ISSUE DATE: 28 May 2013
MANUFACTURER: Opie Manufacturing Group Pty Ltd
PRODUCT DESC: TG3 - Pre Treatment Infloor Channle Drain With Inguilt Arrestor Trap/Kitchen and Food Prep

SLIP RESISTANCE CLASSIFICATION OF NEW PEDESTRIAN SURFACE MATERIALS

OIL-WET RAMP TEST METHOD

TEST CARRIED OUT IN ACCORDANCE WITH
AS/NZS 4586:2004 (Appendix D)

Test Date: 27 May 2013

Location: Slip Resistance Laboratory

Sample Fixed

Joint width: mm

Surface structure: Smooth
 Profiled
 Structured

RESULTS

Mean overall acceptance angle: 19.9 °

Displacement space: not tested

CLASSIFICATION:

Slip Resistance Assessment Group:

R 11 [LOW*]

Displacement Space Assessment Group:

-

* = CSIRO classification



Infrastructure Technology

Manuf. & Materials Technology, 14 Julius Ave (Riverside Corp. Park), North Ryde, NSW, 2113, Australia
Telephone: 61 2 9490 8252 Facsimile: 61 2 9490 5777 Email: tiles@csiro.au Web: http://www.cmse.csiro.au

REPORT NO: 6693.3 Page 3 of 3
ISSUE DATE: 28 May 2013
MANUFACTURER: Opie Manufacturing Group Pty Ltd
TILE DESC: TG3 - Pre Treatment Infloor Channle Drain With Inguilt Arrestor Trap/Kitchen and Food Prep

Date and Place 28 May 2013, North Ryde, NSW

Name, Title and Digital Signature:



BABAK NAVAK
Materials Scientist
Tel: 61 2 94908252
Fax: 61 2 94905777
Email: Babak.Navak@csiro.au

***CSIRO recommended classification of Slip Resistance as determined from:
AS/NZS 4586: 2004 Slip Resistance Classification of New Pedestrian Surface Materials (Appendices A & D).**

Wet Pendulum Class	BPN 4S Rubber	CSIRO Class LOW	CSIRO Class MEDIUM	CSIRO Class HIGH
V	>54	54-57	58-61	>61
W	45-54	45-48	49-51	52-54
X	35-44	35-38	39-41	42-44
Y	25-34	25-28	29-31	32-34
Z	<25	<18	18-21	22-25
Oil Wet Ramp Class	Angle (degrees)	CSIRO Class LOW	CSIRO Class MEDIUM	CSIRO Class HIGH
R9	≥6 to <10	≥6 to 7.5	7.6 to 9	9.1 to 9.9
R10	≥10 to <19	≥10 to 12	12.1 to 15	15.1 to 18.9
R11	≥19 to <27	≥19 to 21	21.1 to 24	24.1 to 26.9
R12	≥27 to <35	≥27 to 29	29.1 to 32	32.1 to 34.9
R13	≥35	≥35 to 36	36.1 to 38	≥38.1

This table should not be read or relied upon without reference to the CSIRO/Standards Australia publication:
AS/NZS 4586 Slip Resistance Classification of New Pedestrian Surface Materials (Appendices A & D).

CSIRO has categorized the AS4586 classifications into sub-groups Low, Medium & High. The slip resistance test classification is still determined according to AS 4586 Australian Standard (Appendices A & D). The added information of Low, Medium and High allows professionals to make a better judgement of pedestrian floor requirements.